

Fusil® SDT155

Precipitated Silica

Fusil® SDT155 is precipitated silica for rubber grade, the appearance is white powder.

Characteristic physico-chemical data

| Item | Units | Specification |
|-------------------------------------|-------|---------------|
| BET | m2/g | 140~160 |
| SiO2 (dry basis) | % | ≥96 |
| Heating Loss 105°C 2h | % | 4.0~8.0 |
| Ignition Loss (dry basis) 1000°C 2h | % | ≤7.0 |
| Soluble Salts (in form of Na2SO4) | % | ≤2.0 |
| PH(5% Solution) | | 6.0~7.5 |
| DBP | cm3/g | 2.0-3.0 |
| Sieve Residue on 45µm | % | ≤0.5 |
| Copper | mg/kg | ≤10 |
| Mn | mg/kg | €50 |
| Fe | mg/kg | ≤500 |

Applications

Rubber products

Properties

It is used as reinforcing agent for a variety of rubber products, e.g. rubber roller, tire, rubber tube, rubber belt, sealing element, rubber sole etc. It gives rubber products higher tear resistance, tensile resistance and transparency.

Safety & Handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Fuchang Chemical, Product Safety Department, E-MAIL info@fuchangchem.com or can check from our homepage www.fuchangchem.com. We recommend to read carefully the safety data sheet prior to the use of our product.

Transportation

20'GP: 6.0 Mt, with pallets

40'HQ: 15.0 Mt, with pallets

Packing and storage

Packaged in multiple layer Kraft paper, 20kg per bag

Stored in aeration-drying storage areas for protecting the material from volatile substance.

Should be used within 2 years after production.

Service

Email: info@fuchangchem.com

Tel: 0086-411-83607405

Website: www.fuchangchem.com



