

# Fusil® SDT185GR

## **Precipitated Silica**

Fusil ® SDT185GR is precipitated silica for rubber grade, the appearance is white granula.

## Characteristic physico-chemical data

Item	Units	Specification
BET	m2/g	161~190
SiO2 (dry basis)	%	≥96
Heating Loss 105℃		
2h	%	4.5~7.5
Ignition Loss		
(dry basis) 1000°C 2h	%	≤7.0
Soluble Salts (in form		
of Na2SO4)	%	≤2.0
PH(5% Solution)		6.0~7.5
DBP	cm3/g	2.0-3.5
Sieve Residue on		
45µm	%	≤0.5
Copper	mg/kg	≤10
Mn	mg/kg	€50
Fe	mg/kg	≤500

# Applications

Rubber products

## Packing and storage

- Packaged in multiple layer Kraft paper, 10kg per bag
- Stored in aeration-drying storage areas for protecting the material from volatile substance.
- Should be used within 2 years after production.

## **Properties**

 It is used as reinforcing agent for a variety of rubber products, e.g. rubber roller, tire, rubber tube, rubber belt, sealing element, rubber sole etc. It gives rubber products higher tear resistance, tensile resistance and transparency.

#### Safety & Handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Fuchang Chemical, Product Safety Department, E-MAIL info@fuchangchem.com or can check from our homepage www.fuchangchem.com. We recommend to read carefully the safety data sheet prior to the use of our product.

## Transportation

• 20'GP: 7.5 Mt, without pallets

• 40'HQ: 18 Mt, without pallets

#### Service

Email: info@fuchangchem.com

Tel: 0086-411-83607405

Website: www.fuchangchem.com

